WHAT IS CLAIMED IS:

1. A fabric material processing method comprising the steps of:

(a) Coating the surface of each of top and bottom sides of a prepared fabric material with a layer of nanostructured metal liquid;

(b) Drying said fabric material;

(c) Dipping said fabric material in a nanostructured water repellant solution to absorb water repellant;

(d) Drying said fabric material;

(e) Spraying a solvent on the surface of the bottom side of said fabric material to remove water repellant from the surface of the bottom side of said fabric material;

(f) Grinding the surface of the bottom side of said fabric material with a grinding wheel before drying of said solvent, so as to remove nanostructured metal from the surface of the bottom side of said fabric material;]

(g) Drying said fabric material and then desizing said fabric material;

(h) Washing said fabric material with clean water; and

(i) Drying said fabric material.

2. The fabric material processing method as claimed in claim 1, wherein said nanostructured metal liquid is a water solution containing 1% nanostructured titanium dioxide (TiO_2), and 10% water soluble dextrin.

3. The fabric material processing method as claimed in claim 1, wherein said nanostructured metal liquid is a water solution containing 1% nanostructured silicon dioxide (SiO_2), and 10% water soluble dextrin.

4. The fabric material processing method as claimed in claim 1, wherein said

nanostructured metal liquid is a water solution containing 1% nanostructured zinc dioxide (ZnO_2), and 10% water soluble dextrin.

5. The fabric material processing method as claimed in claim 1, wherein said nanostructured metal liquid is a water solution containing 1% nanostructured titanium dioxide (TiO_2), and 10% polyethylene.

6. The fabric material processing method as claimed in claim 1, wherein said nanostructured metal liquid is a water solution containing 1% nanostructured silicon dioxide (SiO_2), and 10% polyethylene.

7. The fabric material processing method as claimed in claim 1, wherein said nanostructured metal liquid is a water solution containing 1% nanostructured zinc dioxide (ZnO_2), and 10% polyethylene.

8. The fabric material processing method as claimed in claim 1, wherein said nanostructured water repellant solution is a methylbenzene solution containing 1% nanostructured metal, 1% stearate, and 1.2% silicon water repellant.

9. The fabric material processing method as claimed in claim 1, wherein said nanostructured water repellant solution is an iso-acetone solution containing 1% nanostructured metal, 1% stearate, and 1.2% silicon water repellant.

10. A fabric material processing method comprising the steps of (a) mixing a nanostructured metal with a nanostructured resin to form a nanostructured solution, (b) spraying said nanostructured solution on the top surface of a fabric material and then drying said fabric material, and (c) repeating step (a) and step (b) three times.